



TEMP-COAT® Brand Products, LLC

P.O. Box 725

LaPlace, LA 70069-0725

(985)651-2911 ♦ Fax (985)651-2964

1-800-950-9958 ♦ TEMPCOAT@AOL.COM

Q 2 is the New Rust Stopper! Cleans, Protects, Beautifies. It is inexpensive, completely safe to use, easy to apply and durable. Don't replace those costly items because they are rusty, **Q 2** them. You'll love the **Q 2** easy-one-step application: stops rust and coats in one step.

Use **Q 2** to stop rust on the following:

Agricultural Equipment	Maritime Equipment
Aircraft	Military Equipment
Automobile Restoration	Motorcycles
Bar-B-Que Pits	Motor Homes
Bath Tubs	Port and Harbor Equipment
Bicycles	Snow Mobiles
Boats	Tractors
Electrical Terminals	Trailers
Fleet Equipment	Trucks
Lawn Furniture	Yard Equipment

And much, much more!

ESTIMATED COVERAGE AREA 384 SQ/FT PER GALLON

Prepare

Remove flaking paint and scaly rust with brush or sand paper. It is not necessary to remove or pre-treat normal rusty areas.

Apply

Q 2 may be applied by brush, roller, spray or by dipping rusty object in bath. Apply generously to rusted area and allow to dry. Rusty areas will turn black in 15 to 20 minutes. Re-apply, if necessary, to achieve a uniform, glossy finish.

Paint

Q 2 coating can serve as a primer or undercoating for paint . Suitable paint may be applied to surface in 4-6 hours.

Typical Properties

Physical State @ 77 Degrees F	Liquid
Active Content, %	59
PH, 5% solution in 3:1 IPA/water	0.5
Pour Point, Degrees F	0
Flash Point, TCC Degrees F	210
Specific Gravity @ 77 Degrees F	1.086
Density @ 77 Degrees F, lb./gal.	9.05
Solubility, 10% in:	
Water Dispersible	
Xylene Insoluble	
Isopropyl Alcohol Dispersible	